

## TOP COAT DECORATIVE PRODUCT WITH PRISMATIC PEARL



### DESCRIPTION

DECOPIA is an acrylic emulsion based, decorative protective interior primer finishing paint that contains of three-dimensional prismatic mother-of-pearls and is composed of the mixture of special glitters reflecting different colors and sparkling depending on the light.

### APPLICATION AREA

It is used for decoration and protection on already painted and newly painted surfaces such as wooden, sheet-rock, plasterboards, chipboards, pre-cast concrete panels, satin plasters.

### SURFACE PREPARATION

After all kinds of dirt, oil, bloated paints and dust are cleaned from the surfaces it will be applied on, surface defects should be smoothed with SAN DECO ACRYLIC PUTTY INTERIOR and primed with SAN DECO UNIPRIMER.

Depending on the color chart color, it is recommended to use the product SAN DECO DECOPLAS, which is a matte interior wall paint.

The recommended matte paint, DECOPLAS should be diluted with no more than 20% of clean water by volume and applied in 2 layers with a roller or brush without leaving any traces. It is mandatory to wait at least 4 hours between layers.

### FEATURES

- It reflects 3 different colors depending on the light and perspective because of special prismatic mother-of-pearls it contains.
- It can be wiped off with water.
- Due to the strong water vapor permeability, it allows vapor to be released outside and the surface to breathe.
- It does not harm human health and environment as it is water-based.
- It allows environments of application to smell nice due to its perfume characteristic.

### The Product

Composition	Acrylic Based
Density	1.02 g/cm <sup>3</sup>
	8,51 lbs./gallon
Storage Temperature	5 °C + 35 °C 41 °F + 95 °F
Emission Limits of Volatile Organic Compounds (VOC) According to Directive 2004/42/CE	Subcategory: L VOC: 48 g/l (max); Limit Phase : 200 g/l
Theoretical Coverage (Single Coat)	671 – 814 sq. Ft/gallon
	16,5 – 20,0 m <sup>2</sup> /L
Weight Per Gallon	8,51 lbs.
Packaging	1 Pint

### The Application

Dilution	3-5% (Clean Water)
Surface Preparation	San Deco Acrylic Putty Interior
Primer	San Deco Decoprimer or San Deco Decoplas
Application Tools	Roller, Brush
Touch Dry Time	2-3 Hours
Complete Dry Time	24 Hours
Dry Time Temperature	23 °C - 73.4°F (relative humidity at 50%)
Application Temperature (24 hours during and after the application)	5 °C + 35 °C 41 °F + 95 °F

## APPLICATION INSTRUCTION

- After the sub-base dries, DECOPIA is applied in one layer with a brush or roller to the surface, mixing it uniformly with the addition of clean water of no more than 3-5% by volume. The preferred method of application is the application of a special brush.
- It should be paid attention that the ambient temperature should be minimum +5°C, and maximum +35°C within 24 hours during and after the application.

## DRYING TIME

At 23°C, the touching time is 2-3 hours and the complete drying time is 24 hours.

## THEORETICAL CONSUMPTION

For one-layer application, depending on the surface smoothness, absorbency and application techniques;

-16,5 - 20,0 m<sup>2</sup> with 1 lt.,

-16,5 - 20,0 m<sup>2</sup> area is painted with 1 kg.,

- Paint consumption for an area of 1 m<sup>2</sup> is 50 - 60 ml. and 50 - 60 gr.

## STORAGE

It can be stored in its unopened package, cool and dry environments, protected from direct sunlight at between +5°C and +35°C.



## HAZARD STATEMENTS

- H317 May cause an allergic skin reaction

## PRECAUTIONARY STATEMENTS

- P261 Avoid breathing dust/fume/gas/mist/vapours/spray.
- P272 Contaminated work clothing should not be allowed out of the workplace.
- P280 Wear protective gloves/protective clothing/eye protection/face protection.
- P302 + P352 IF ON SKIN: Wash with plenty of soap and water.
- P333 + P313 If skin irritation or rash occurs: Get medical advice/attention.
- P363 Wash contaminated clothing before reuse.
- EUH208 Contains chloromethylisothiazolinone and methylisothiazolinone (3:1) May produce an allergic reaction.

Note: For more information, please check the Safety Data Sheet (SDS) of the product

## Product Technical Data Sheet No. DP. 025.US - Rev01 January 2022

Since this technical sheet is prepared on the basis of laboratory data under normal conditions, consult the technical staff for details that are not sufficient above. Otherwise, errors that will occur as a result of insufficient information do not impose responsibility on the manufacturer. Deka Boya San. ve Tic. A.S. reserves the right to change this information. If necessary, you can find detailed information about the health safety-transportation risks and precautions of the products from the Material Safety Data Sheet.

**This product is produced by Deka Boya Sanayi ve Tic. A.S. who is also certified by the standards of ISO 9001, ISO 14001, ISO 27001, ISO 45001.**