

INTERIOR EFFECT PAINT PRIMER



DESCRIPTION

DECOPRIMER is acrylic emulsion based and a special primer formulized to increase adhesion of decorative products to surfaces.

APPLICATION AREA

It is used as primer of acrylic-based decorative coating materials used on mineral surfaces such as all kinds of concrete, aerated concrete, pressed brick, finish and gypsum plaster.

SURFACE PREPARATION

After all kinds of dirt, oil, blistered paint and dust are cleaned from the surfaces of application, the surface defects should be smoothed with SAN DECO ACRYLIC PUTTY INTERIOR, if any.

FEATURES

- It creates a smooth surface
- It adheres to the surface perfectly and prepares the ground for the decorative materials to be applied.
- It is high coverage.
- It is water-based, does not smell or not harm human health and environment.

The Product

Composition	Acrylic Based
Density	1.57 g/cm ³
	13,10 lbs./gallon
Storage Temperature	5 °C ÷ 35 °C 41 °F ÷ 95 °F
Emission Limits of Volatile Organic Compounds (VOC) According to Directive 2004/42/CE	Subcategory: G VOC: 23 g/l (max); Limit Phase : 30 g/l
Theoretical Coverage (Single Coat)	427 – 610 sq. Ft/gallon
	10,5 – 15,0 m ² /L
Weight Per Gallon	13,10 lbs.
Packaging	1 Quart, 1 Gallon, 3 Gallon

The Application

Dilution	25-30% (Clean Water)
Surface Preparation	San Deco Acrylic Putty Interior
Application Tools	Roller
Touch Dry Time	2-3 Hours
Complete Dry Time	24 Hours
Dry Time Temperature	23 °C - 73.4°F (relative humidity at 50%)
Application Temperature (24 hours during and after the application)	5 °C ÷ 35 °C 41 °F ÷ 95 °F

APPLICATION INSTRUCTION

- Before application, the DECOPRIMER is diluted with 25-30% clean water by volume and mixed mechanically until it becomes homogeneous.
- DECOPRIMER is applied to the surface with a roller in one layer.
- It should be paid attention that the ambient temperature should be minimum +5°C/41 °F, and maximum +35°C/95 °F within 24 hours during and after the application.

DRYING TIME

At 23°C/73.4°F, the touching time is 2-3 hours and the complete drying time is 24 hours.

THEORETICAL CONSUMPTION

For one-layer application, depending on the surface smoothness, absorbency and application techniques;

-10,5 – 15,0 m² with 1 lt.,

-6,5 – 10,0 m² area is painted with 1 kg.,

- Paint consumption for an area of 1 m² is 65 – 100 ml. and 100 – 150 gr.

STORAGE

It can be stored in its unopened package, cool and dry environments, protected from direct sunlight at between +5°C/41 °F and +35°C/95 °F.



HAZARD STATEMENTS

- H317 May cause an allergic skin reaction

PRECAUTIONARY STATEMENTS

- P261 Avoid breathing dust/fume/gas/mist/vapours/spray.
- P272 Contaminated work clothing should not be allowed out of the workplace.
- P280 Wear protective gloves/protective clothing/eye protection/face protection.
- P302 + P352 IF ON SKIN: Wash with plenty of soap and water.
- P333 + P313 If skin irritation or rash occurs: Get medical advice/attention.
- P363 Wash contaminated clothing before reuse.
- EUH208 Contains: chloromethylisothiazolinone and methylisothiazolinone (3:1); 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1); 2-methylisothiazol-3(2H)-one and 1,2-benzisothiazol-3(2H)-one.includes. May produce an allergic reaction.
- EUH210 Safety data sheet available on request
- EUH211 Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist.

Note: For more information, please check the Safety Data Sheet (SDS) of the product

Product Technical Data Sheet No. DP. 032.US - Rev01 January 2022

Since this technical sheet is prepared on the basis of laboratory data under normal conditions, consult the technical staff for details that are not sufficient above. Otherwise, errors that will occur as a result of insufficient information do not impose responsibility on the manufacturer. Deka Boya San. ve Tic. A.S. reserves the right to change this information. If necessary, you can find detailed information about the health safety-transportation risks and precautions of the products from the Material Safety Data Sheet.

This product is produced by Deka Boya Sanayi ve Tic. A.S. who is also certified by the standards of ISO 9001, ISO 14001, ISO 27001, ISO 45001.