

MARBLE EFFECT VENETIAN PLASTER



DESCRIPTION

DECOSTUCCO is an acrylic emulsion based, pasty, interior decorative coating material with a glossy finish, which contains various types of quartz limestone and pigments, is given its texture and form with a trowel or spatula.

APPLICATION AREA

It is used together with the appropriate primer on walls, plasters, gross concrete and wooden surfaces after surface preparation.

SURFACE PREPARATION

After all kinds of dirt, oil, bloated paints and dust are cleaned from the surfaces it will be applied on, surface defects should be smoothed with SAN DECO ACRYLIC PUTTY INTERIOR and already-painted surfaces should be primed with SAN DECO DECOPRIMER as well as surfaces to be newly painted.

FEATURES

- The product derives a marble looking effect to the surface on which it is applied.
- Due to its high brightness, the colors are vivid and sparkling.
- Due to the strong water vapor permeability, it allows vapor to be released outside and the surface to breathe.
- It does not harm human health and environment as it is water-based.
- It allows environments of application to smell nice due to its perfume characteristic.

The Product

| | |
|---|---|
| Composition | Acrylic Based, Quartz Limestone and Pigments |
| Density | 1.56 g/cm ³ |
| | 13,01 lbs./gallon |
| Storage Temperature | 5 °C + 35 °C 41 °F + 95 °F |
| Emission Limits of Volatile Organic Compounds (VOC) According to Directive 2004/42/CE | Subcategory: L VOC: 70 g/l (max); Limit Phase : 200 g/l |
| Theoretical Coverage | 116 – 175 sq. Ft/gallon |
| | 2,85 – 4,30 m ² /L |
| Weight Per Gallon | 13,01 lbs. |
| Packaging | 1 Gallon, 3 Gallon |

The Application

| | |
|---|---|
| Dilution | Ready To Use |
| Surface Preparation | San Deco Acrylic Putty Interior |
| Primer | San Deco Decoprimer |
| Application Tools | Steel Trowel |
| Touch Dry Time | 2-3 Hours |
| Complete Dry Time | 24 Hours |
| Dry Time Temperature | 23 °C - 73.4°F (relative humidity at 50%) |
| Application Temperature (24 hours during and after the application) | 5 °C + 35 °C 41 °F + 95 °F |

APPLICATION INSTRUCTION

- Prior to the application, DECOSTUCCO is thoroughly mixed.
- The product is applied to the surface with a steel trowel in 1 layer; if the necessary sealing is not achieved on the surface, second layer is applied.
- When the material dries 24 hours after application, the surface is sanded with a fine sandpaper and the intended effect is applied with a trowel or spatula. The surface is pressed with a steel trowel and polished.
- It should be paid attention that the ambient temperature should be minimum +5°C/41°F, and maximum +35°C/95°F within 24 hours during and after the application.

DRYING TIME

At 23°C/73.4°F, the touching time is 2-3 hours and the complete drying time is 24 hours.

THEORETICAL CONSUMPTION

Depending on the surface smoothness, absorbency and application techniques, the consumption;
-2,85 – 4,30 m² with 1 lt.,

-1,65 – 2,50 m² area is painted with 1 kg.,

- Paint consumption for an area of 1 m² is 230 – 350 ml. and 400 – 600 gr.

STORAGE

It can be stored in its unopened package, cool and dry environments, protected from direct sunlight at between +5°C/41°F and +35°C/95°F.



HAZARD STATEMENTS

- H317 May cause an allergic skin reaction

PRECAUTIONARY STATEMENTS

- P261 Avoid breathing dust/fume/gas/mist/vapours/spray.
- P272 Contaminated work clothing should not be allowed out of the workplace.
- P280 Wear protective gloves/protective clothing/eye protection/face protection.
- P302 + P352 IF ON SKIN: Wash with plenty of soap and water.
- P333 + P313 If skin irritation or rash occurs: Get medical advice/attention.
- P363 Wash contaminated clothing before reuse.
- EUH208 Contains chloromethylisothiazolinone and methylisothiazolinone (3:1) May produce an allergic reaction.

Note: For more information, please check the Safety Data Sheet (SDS) of the product

Product Technical Data Sheet No. DP. 014.US - Rev01 January 2022

Since this technical sheet is prepared on the basis of laboratory data under normal conditions, consult the technical staff for details that are not sufficient above. Otherwise, errors that will occur as a result of insufficient information do not impose responsibility on the manufacturer. Deka Boya San. ve Tic. A.S. reserves the right to change this information. If necessary, you can find detailed information about the health safety-transportation risks and precautions of the products from the Material Safety Data Sheet.

This product is produced by Deka Boya Sanayi ve Tic. A.S. who is also certified by the standards of ISO 9001, ISO 14001, ISO 27001, ISO 45001.

SAN DECO

Paint Manufacturing & Distribution

Headquarters: Yukarı Dudullu Mah. Necip Fazıl Bulvarı Keyap Çarşısı D2 Blok No:61 Ümraniye/İstanbul

Contact: +1 786-224-14-64