

**PASTY DECORATIVE COATING
COMBINED WITH FINISHING PAINT**



DESCRIPTION

MIRZASTO is an acrylic emulsion based, pasty, special decorative coating that is easy to apply and easily patterned.

APPLICATION AREA

It is used with EFFECT FINISH, which is the appropriate primer and finishing material after surface preparation, on walls, plasters, gross concretes and wooden surfaces in interiors of buildings.

SURFACE PREPARATION

After all kinds of dirt, oil, bloated paints and dust are cleaned from the surfaces it will be applied on, surface defects should be smoothened with SAN DECO ACRYLIC PUTTY INTERIOR and primed with SAN DECO DECOPRIMER.

FEATURES

- Thanks to the special fillings available in it, it is easily applied and patterned.
- It is easy to sand it and get the desired texture.
- In MIRZASTO application, there are no difficulties of application caused by premature drying due to the structure of the product.
- Due to the strong water vapor permeability, it allows water vapor to be released outside and the surface to breathe.
- It does not harm human health and environment as it is water-based.

The Product

| | |
|---|---|
| Composition | Acrylic Based |
| Density | 1.70 g/cm ³ |
| | 14,18 lbs./gallon |
| Storage Temperature | 5 °C ÷ 35 °C 41 °F ÷ 95 °F |
| Emission Limits of Volatile Organic Compounds (VOC) According to Directive 2004/42/CE | Subcategory: L VOC: 46 g/l (max); Limit Phase : 200 g/l |
| Theoretical Coverage (Single Coat) | 163 – 204 sq. Ft/gallon |
| | 4– 5 m ² /L |
| Weight Per Gallon | 14,68 lbs. |
| Packaging | 1 Gallon |

The Application

| | |
|---|---|
| Dilution | Ready To Use |
| Surface Preparation | San Deco Acrylic Putty Interior |
| Primer | San Deco Decoprimer |
| Application Tools | Steel Trowel, Sandpaper |
| Touch Dry Time | 4-5 Hours |
| Complete Dry Time | 24 Hours |
| Dry Time Temperature | 23 °C - 73.4°F (relative humidity at 50%) |
| Application Temperature (24 hours during and after the application) | 5 °C ÷ 35 °C 41 °F ÷ 95 °F |

APPLICATION INSTRUCTION

- MIRZASTO should be mixed homogeneously without being diluted.
- MIRZASTO is applied in single layer with a steel trowel. After being applied on an area of 1-2m², striped or irregular patterns are formed with a steel trowel or plastic apparatus. Mirzasto application continues by this method.
- After waiting 4 hours at, the surface is sanded with a sandpaper to remove irregular bulges (220/260) and dusted off. Then, according to the color chart, the EFFECT FINISH coming first color is applied with a trowel. It is required to wait 3 hours and then, the EFFECT FINISH product coming second is applied with a steel trowel and the application is completed.
- It should be paid attention that the ambient temperature should be minimum +5°C/ 41 °F, and maximum +35°C/ 95 °F within 24 hours during and after the application.

DRYING TIME

At 23°C/73.4°F, the touching time is 4-5 hours and the complete drying time is 24 hours.

THEORETICAL CONSUMPTION

For one-layer application, depending on the surface smoothness, absorbency and application techniques;
-4,0 - 5,0 m² with 1 lt.
-2,3 - 2,9 m² area is painted with 1 kg.
- Paint consumption for an area of 1 m² is 200 - 250 ml and 350 - 450 gr.

STORAGE

It can be stored in its unopened package, cool and dry environments, protected from direct sunlight at between +5°C/ 41 °F and +35°C/ 95 °F.



HAZARD STATEMENTS

- H317 May cause an allergic skin reaction

PRECAUTIONARY STATEMENTS

- P261 Avoid breathing dust/fume/gas/mist/vapours/spray.
- P272 Contaminated work clothing should not be allowed out of the workplace.
- P280 Wear protective gloves/protective clothing/eye protection/face protection.
- P302 + P352 IF ON SKIN: Wash with plenty of soap and water.
- P333 + P313 If skin irritation or rash occurs: Get medical advice/attention.
- P363 Wash contaminated clothing before reuse.
- EUH208 Contains chloromethylisothiazolinone and methylisothiazolinone (3:1). May produce an allergic reaction.

Note: For more information, please check the Safety Data Sheet (SDS) of the product

Product Technical Data Sheet No. DP. 022.US - Rev01 January 2022

Since this technical sheet is prepared on the basis of laboratory data under normal conditions, consult the technical staff for details that are not sufficient above. Otherwise, errors that will occur as a result of insufficient information do not impose responsibility on the manufacturer. Deka Boya San. ve Tic. A.S. reserves the right to change this information. If necessary, you can find detailed information about the health safety-transportation risks and precautions of the products from the Material Safety Data Sheet.

This product is produced by Deka Boya Sanayi ve Tic. A.S. who is also certified by the standards of ISO 9001, ISO 14001, ISO 27001, ISO 45001.