

TRAVERTINE DECORATIVE COATING



DESCRIPTION

TRAVERTINO is a mineral-based, natural, decorative interior wall coating material that allows a travertine look to be obtained on the surface it is applied.

APPLICATION AREA

It is used on walls, plasters, gross concretes and wooden surfaces indoors together with the appropriate primer after floor preparation.

SURFACE PREPARATION

After all kinds of dirt, oil, bloated paints and dust are cleaned from the surfaces it will be applied on, surface defects should be smoothened with SAN DECO ACRYLIC PUTTY INTERIOR and primed with SAN DECO DECOPRIMER.

FEATURES

- It is a material that allows you to create effects in different textures with the skills of the practitioner during application.
- Due to the strong water vapor permeability, it allows water vapor to be released outside and the surface to breathe.
- It does not harm human health and environment as it is water-based.
- It allows environments of application to smell nice due to its perfume characteristic.

The Product

Composition	Mineral Based
Density	1.76 g/cm ³
	14,68 lbs./gallon
Storage Temperature	5 °C + 35 °C 41 °F + 95 °F
Emission Limits of Volatile Organic Compounds (VOC) According to Directive 2004/42/CE	Subcategory: L VOC: 40 g/l (max); Limit Phase : 200 g/l
Theoretical Coverage (Single Coat)	72 – 96 sq. Ft/gallon
	1,75 – 2,35 m ² /L
Weight Per Gallon	14,68 lbs.
Packaging	3 Gallon

The Application

Dilution	Ready To Use
Surface Preparation	San Deco Acrylic Putty Interior
Primer	San Deco Decoprimer
Application Tools	Steel Trowel
Touch Dry Time	2-3 Hours
Complete Dry Time	48 Hours
Dry Time Temperature	23 °C - 73.4°F (relative humidity at 50%)
Application Temperature (24 hours during and after the application)	5 °C + 35 °C 41 °F + 95 °F

APPLICATION INSTRUCTION

- TRAVERTINO is applied undiluted with a steel trowel so that the first layer is at least 1 mm. thick.
- At least 6 hours after the first coat application, the second coat is applied.
- The surface is given the effect with its special sponge or comb prior to the complete drying of the second coat.
- Then the surface is polished with a steel trowel to obtain a uniform finish.
- It should be paid attention that the ambient temperature should be minimum +5°C/ 41 °F, and maximum +35°C/ 95 °F within 24 hours during and after the application.

DRYING TIME

At 23°C/73.4°F, the touching time is 2-3 hours and the complete drying time is 48 hours.

THEORETICAL CONSUMPTION

For one-layer application, depending on the surface smoothness, absorbency and application techniques;

-1,75 - 2,35 m² with 1 lt.,

-1,00 - 1,35 m² area is painted with 1 kg.

- Paint consumption for an area of 1 m² is 425 - 570ml and 750 - 1000 gr.

STORAGE

It can be stored in its unopened package, cool and dry environments, protected from direct sunlight at between +5°C/ 41 °F and +35°C/ 95 °F.



HAZARD STATEMENTS

- H317 May cause an allergic skin reaction

PRECAUTIONARY STATEMENTS

- P261 Avoid breathing dust/fume/gas/mist/vapours/spray.
- P272 Contaminated work clothing should not be allowed out of the workplace.
- P280 Wear protective gloves/protective clothing/eye protection/face protection.
- P302 + P352 IF ON SKIN: Wash with plenty of soap and water.
- P333 + P313 If skin irritation or rash occurs: Get medical advice/attention.
- P363 Wash contaminated clothing before reuse.
- EUH208 Contains chloromethylisothiazolinone and methylisothiazolinone (3:1) May produce an allergic reaction.

Note: For more information, please check the Safety Data Sheet (SDS) of the product

Product Technical Data Sheet No. DP. 017.US - Rev01 January 2022

Since this technical sheet is prepared on the basis of laboratory data under normal conditions, consult the technical staff for details that are not sufficient above. Otherwise, errors that will occur as a result of insufficient information do not impose responsibility on the manufacturer. Deka Boya San. ve Tic. A.S. reserves the right to change this information. If necessary, you can find detailed information about the health safety-transportation risks and precautions of the products from the Material Safety Data Sheet.

This product is produced by Deka Boya Sanayi ve Tic. A.S. who is also certified by the standards of ISO 9001, ISO 14001, ISO 27001, ISO 45001.