

INTERIOR AND EXTERIOR PRIMER



DESCRIPTION

UNIPRIMER is an acrylic emulsion-based, silicone-added, filled interior and exterior primer.

APPLICATION AREA

It is used as a primer on all types of concrete, aerated concrete, even or uneven all kinds of plastered, mineral-based surfaces, silicone or acrylic-based already-painted surfaces.

SURFACE PREPARATION

After all kinds of dirt, oil, blistered paint and dust are cleaned from the surfaces of application, the surface defects should be smoothed with SAN DECO ACRYLIC PUTTY INTERIOR/EXTERIOR.

FEATURES

- It reduces absorbency and paint consumption of surfaces it is applied on.
- It has a high level of hiding.
- It prevents the paint applied on it from being absorbed differently by the surface, ensuring a full homogeneous spread.
- Thanks to its ability to breathe, it allows moisture inside the structure to go outwards, so it does not crack, swell and spill.
- It can be colored in any desired color.
- It does not harm human health and environment as it is water-based.

The Product

Composition	Acrylic Based and Silicone-added
Density	1.51 g/cm ³
	12,60 lbs./gallon
Storage Temperature	5 °C + 35 °C 41 °F + 95 °F
Emission Limits of Volatile Organic Compounds (VOC) According to Directive 2004/42/CE	Subcategory: G VOC: 29 g/l (max); Limit Phase : 30 g/l
Theoretical Coverage (Single Coat)	468 – 590 sq. Ft/gallon
	11,50 – 14,50 m ² /L
Weight Per Gallon	12,60 lbs.
Packaging	1 Quart, 1 Gallon, 3 Gallon

The Application

Dilution	%20-25 (Clean Water)
Surface Preparation	San Deco Acrylic Putty Interior/Exterior
Application Tools	Roller, Brush or Spray
Touch Dry Time	4-5 Hours
Complete Dry Time	24 Hours
Dry Time Temperature	23 °C - 73.4°F (relative humidity at 50%)
Application Temperature (24 hours during and after the application)	5 °C + 35 °C 41 °F + 95 °F

APPLICATION INSTRUCTION

- Prior to application, UNIPRIMER should be diluted with 20-25% clean water by volume and mixed thoroughly.
- Then the product should be applied in one layer with a roller, brush or by spraying.
- It should be paid attention that the ambient temperature should be minimum +5°C/41 °F, and maximum +35°C/95 °F within 24 hours during and after the application.

DRYING TIME

At 23°C/73.4°F, the touching time is 4-5 hours and the complete drying time is 24 hours.

THEORETICAL CONSUMPTION

For one-layer application, depending on the surface smoothness, absorbency and application techniques;
-11,5 - 14,5 m² with 1 lt,
-7,6 - 9,0 m² area is painted with 1 kg.
- Paint consumption for an area of 1 m² is 70-85 ml. and 110-130 gr.

STORAGE

It can be stored in its unopened package, cool and dry environments, protected from direct sunlight at between +5°C/41 °F and +35°C/95 °F.



HAZARD STATEMENTS

- H317 May cause an allergic skin reaction

PRECAUTIONARY STATEMENTS

- P261 Avoid breathing dust/fume/gas/mist/vapours/spray.
- P272 Contaminated work clothing should not be allowed out of the workplace.
- P280 Wear protective gloves/protective clothing/eye protection/face protection.
- P302 + P352 IF ON SKIN: Wash with plenty of soap and water.
- P333 + P313 If skin irritation or rash occurs: Get medical advice/attention.
- P363 Wash contaminated clothing before reuse.
- EUH208 Contains: chloromethylisothiazolinone and methylisothiazolinone (3:1); 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1); 2-methylisothiazol-3(2H)-one and 1,2-benzisothiazol-3(2H)-one.includes. May produce an allergic reaction.
- EUH210 Safety data sheet available on request
- EUH211 Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist.

Note: For more information, please check the Safety Data Sheet (SDS) of the product

Product Technical Data Sheet No. EP.015.US - Rev01 January 2022

Since this technical sheet is prepared on the basis of laboratory data under normal conditions, consult the technical staff for details that are not sufficient above. Otherwise, errors that will occur as a result of insufficient information do not impose responsibility on the manufacturer. Deka Boya San. ve Tic. A.S. reserves the right to change this information. If necessary, you can find detailed information about the health safety-transportation risks and precautions of the products from the Material Safety Data Sheet.

This product is produced by Deka Boya Sanayi ve Tic. A.S. who is also certified by the standards of ISO 9001, ISO 14001, ISO 27001, ISO 45001.