

## WATER AND WAX EMULSION BASED FINISHING POLISH



### DESCRIPTION

It is a water-based Wax emulsion-based, finishing varnish for DECOSTUCCO.

### APPLICATION AREA

It is applied to decorative materials such as DECOSTUCCO in order to acquire it a shiny marble appearance.

### SURFACE PREPARATION

The surface on which WAX will be applied should be completely dry; and free from first and dust.

### FEATURES

- It increases the gloss of the decorative materials on which it is applied and brings the surface a glossy marble appearance.
- It is applied very easily with the help of a steel trowel.
- It does not harm human health and environment as it is water-based.

The Product	
Composition	Acrylic Based,
Density	1,01 g/cm <sup>3</sup>
	8,42 lbs./gallon
Storage Temperature	5 °C + 35 °C
	41 °F + 95 °F
Emission Limits of Volatile Organic Compounds (VOC) According to Directive 2004/42/CE	Subcategory: L VOC: 20 g/l (max); Limit Phase : 200 g/l
Theoretical Coverage	1017 – 1383 sq. Ft/gallon
	25 – 34 m <sup>2</sup> /L
Weight Per Gallon	8,42 lbs.
Packaging	1 Pint
The Application	
Dilution	Ready To Use
Application Tools	Steel Trowel, Velvet Cloth
Touch Dry Time	30 Minute - 1 Hours
Complete Dry Time	24 Hours
Dry Time Temperature	23 °C - 73.4°F with relative humidity at 50%
Application Temperature (24 hours during and after the application)	5 °C + 35 °C
	41 °F + 95 °F

### APPLICATION INSTRUCTION

- Water-based wax is applied with a steel trowel in 2 layers on surfaces where DECOSTUCCO application is completed. It is required to wait 30 minutes - 1 hour at 23 °C/73.4°F between layers.
- The second layer is applied by being polished with a velvet cloth before it dries completely.
- It should be paid attention that the ambient temperature should be minimum +5°C/ 41 °F, and maximum +35°C/ 95 °F within 24 hours during and after the application.

### DRYING TIME

At 23°C/73.4°F, the touching time is 30 minutes to 1 hour and the complete drying time is 24 hours

### THEORETICAL CONSUMPTION

For application, depending on the surface smoothness, approximately:

-25,0 – 34,0 m<sup>2</sup> with 1 lt.,

-25,0 – 34,0 m<sup>2</sup> area is painted with 1 kg.,

- Paint consumption WAX consumption for an area of 1 m<sup>2</sup> is 30 -40 ml and 30 -40 gr.

### STORAGE

It can be stored in its unopened package, cool and dry environments, protected from direct sunlight at between +5°C/ 41 °F and +35°C/ 95 °F.



### HAZARD STATEMENTS

- H317 May cause an allergic skin reaction

### PRECAUTIONARY STATEMENTS

- P261 Avoid breathing dust/fume/gas/mist/vapours/spray.
- P272 Contaminated work clothing should not be allowed out of the workplace.
- P280 Wear protective gloves/protective clothing/eye protection/face protection.
- P302 + P352 IF ON SKIN: Wash with plenty of soap and water.
- P333 + P313 If skin irritation or rash occurs: Get medical advice/attention.
- P363 Wash contaminated clothing before reuse.
- EUH208 Contains chloromethylisothiazolinone and methylisothiazolinone (3:1) May produce an allergic reaction.

Note: For more information, please check the Safety Data Sheet (SDS) of the product

### Product Technical Data Sheet No. DP. 029.US - Rev01 January 2022

Since this technical sheet is prepared on the basis of laboratory data under normal conditions, consult the technical staff for details that are not sufficient above. Otherwise, errors that will occur as a result of insufficient information do not impose responsibility on the manufacturer. Deka Boya San. ve Tic. A.S. reserves the right to change this information. If necessary, you can find detailed information about the health safety-transportation risks and precautions of the products from the Material Safety Data Sheet.

**This product is produced by Deka Boya Sanayi ve Tic. A.S. who is also certified by the standards of ISO 9001, ISO 14001, ISO 27001, ISO 45001.**